

Design And Development of Self-Healing Nanocomposites for High-Performance Applications in Extreme Environments

Authors Details

Michael Ayobami Akinlabi¹

Department of Materials and Metallurgical Engineering, Faculty of Engineering and Technology, University of Ilorin, Ilorin, Kwara State. Nigeria.

Mubarak Olanrewaju Abdulrasak²

Department of Materials and Metallurgical Engineering, Faculty of Engineering and Technology, University of Ilorin, Ilorin, Kwara State. Nigeria.

Jeremiah Oluwayomi Oladetan³

Department of Aerospace Engineering, Faculty of Engineering, Lagos State University, Ojo, Lagos State, Nigeria.

Michael Abimbola Oladosu^{4*}

Department of Chemical Sciences, Faculty of Science, Anchor University, Ayobo, Lagos State, Nigeria.

Moses Adondua Abah⁵

Department of Biochemistry, Faculty of Pure and Applied Sciences, Federal University of Wukari, Wukari, Taraba State, Nigeria.

Olaide Ayokunmi Oladosu⁶

Department of Computer Science, Faculty of Science and Technology, Babcock University, Ilishan, Nigeria.

Babatunde John Agbajeola⁷

Department of Material and Metallurgical Engineering, Faculty of Engineering, University of Lagos, Akoka, Lagos, Nigeria.

Angel Ojimaajo Ekele⁸

Department of Biochemistry, Faculty of Pure and Applied Sciences, Federal University of Wukari, Wukari, Taraba State, Nigeria.

Corresponding Author: *Michael Abimbola Oladosu*

ABSTRACT: Self-healing nanocomposites represent a paradigm shift in materials science, offering autonomous damage repair capabilities crucial for high-performance applications in extreme environments. This review examines recent advances (2020-2025) in the design, synthesis, and characterization of self-healing nanocomposite systems engineered for operation under harsh conditions including elevated temperatures, aggressive chemical exposure, mechanical stress, and radiation environments. We comprehensively analyse intrinsic and extrinsic healing mechanisms, including dynamic covalent bonding, supramolecular interactions, microcapsule-based systems, and vascular networks integrated with nanoscale reinforcements. The synergistic effects of nanofillers such as graphene, carbon nanotubes, metal-organic frameworks, and ceramic nanoparticles on mechanical properties, thermal stability, and healing efficiency are critically evaluated. Applications in aerospace, energy storage, protective coatings, and biomedical devices are discussed, highlighting the multifunctional performance requirements. Current challenges including healing kinetics at low temperatures, repeated healing cycles, and scalability for industrial production are addressed. This review provides insights into future directions for developing next-generation autonomous materials capable of extending service life and enhancing reliability in demanding operational conditions.

Keywords: *Self-healing polymers, Nanocomposites, Extreme environments, Autonomous repair, Dynamic chemistry, Nanomaterials.*

1. Introduction

The development of advanced materials capable of autonomous damage repair has emerged as a critical frontier in materials science and engineering, particularly for applications demanding exceptional reliability in extreme operational environments [1,2]. Self-healing nanocomposites integrate the autonomous repair capabilities of responsive polymer matrices with the superior mechanical, thermal, and functional properties imparted by nanoscale reinforcements, creating multifunctional material systems that can recover from damage while maintaining high performance under harsh conditions [3,4]. Traditional materials in extreme environments, characterized by elevated temperatures, corrosive atmospheres, intense radiation, or severe mechanical loads, are prone to microcrack formation, interfacial delamination, and progressive degradation that ultimately compromise structural integrity and functional performance [5,6].

The incorporation of self-healing mechanisms into nanocomposite systems addresses a fundamental limitation of conventional materials: the inability to arrest damage propagation autonomously, which necessitates frequent inspection, maintenance, and replacement, particularly in applications where accessibility is limited or failure consequences are catastrophic [7,8]. Recent advances in dynamic chemistry, supramolecular design, and nanomaterial engineering have enabled the development of self-healing nanocomposites with remarkable healing efficiencies, rapid response times, and the capacity for multiple healing cycles [9,10]. These materials find applications across diverse sectors including aerospace structures subjected to thermal cycling and micrometeorite impacts, energy storage systems operating under electrochemical stress, protective coatings exposed to corrosive environments, and biomedical implants requiring biocompatibility alongside mechanical durability [1,12].

This review provides a comprehensive analysis of recent developments (2020-2025) in self-healing nanocomposite design, focusing specifically on systems engineered for extreme environment performance. We examine the fundamental healing mechanisms, nanocomposite architectures, characterization methodologies, and application-specific considerations that define this rapidly evolving field.

2. Self-Healing Mechanisms in Nanocomposite Systems

2.1 Intrinsic Self-Healing Approaches

Intrinsic self-healing mechanisms rely on the inherent reversibility of chemical bonds or physical interactions within the polymer matrix, enabling autonomous repair without external healing agents [13]. Dynamic covalent chemistry, including Diels-Alder cycloaddition, disulfide exchange, imine bond formation, and boronic ester transesterification, has been extensively implemented to create thermally reversible networks capable of multiple healing cycles [14,15]. These systems exhibit particular promise for high-temperature applications, as elevated temperatures accelerate bond exchange kinetics while maintaining network integrity through dynamic equilibrium [16].

Supramolecular self-healing mechanisms based on hydrogen bonding, metal-ligand coordination, π - π stacking, and host-guest interactions offer advantages of healing at ambient or reduced temperatures with minimal external stimulation [17,18]. The

integration of nanofillers into these intrinsically healable matrices presents both opportunities and challenges: nanoparticles can serve as multifunctional crosslinking nodes, stress concentration sites that trigger localized healing responses, or interfacial modifiers that enhance polymer-filler adhesion [19]. Recent studies have demonstrated that graphene oxide functionalized with complementary hydrogen-bonding groups can simultaneously reinforce the polymer matrix and participate in the self-healing network, achieving healing efficiencies exceeding 90% while maintaining mechanical properties suitable for structural applications [20,21].

2.2 Extrinsic Self-Healing Strategies

Extrinsic self-healing approaches incorporate discrete healing agents, typically encapsulated in microcapsules or embedded within vascular networks, that are released upon damage to fill cracks and restore material continuity [22]. Microencapsulation techniques have evolved to produce core-shell structures with precisely controlled shell permeability, payload composition, and release kinetics optimized for specific damage scenarios [23]. The healing agent selection is crucial for extreme environment applications, requiring thermal stability, chemical compatibility with the matrix, appropriate viscosity for crack infiltration, and polymerization or crosslinking mechanisms that function under operational conditions [24].

Nanoparticles play multiple roles in extrinsic self-healing systems: as capsule shell reinforcements to control permeability and mechanical triggering thresholds, as catalysts for healing agent polymerization, or as thermal management agents to dissipate localized heating during damage events [25,26]. Vascular networks, inspired by biological circulatory systems, provide continuous healing agent delivery and enable repeated repair of the same location, addressing a key limitation of microcapsule-based systems [27]. Recent innovations include 3D-printed vascular architectures with hierarchical channel dimensions and nanoparticle-functionalized healing agents that exhibit enhanced flow properties and crosslinking kinetics [28]. Table 1 shows the Comparison of intrinsic and extrinsic self-healing mechanisms for extreme environment applications.

Table 1. Comparison of intrinsic and extrinsic self-healing mechanisms for extreme environment applications

Healing Mechanism	Key Chemistry	Healing Temperature Range	Healing Efficiency (%)	Multiple Cycles	Primary Advantages	Limitations
Diels-Alder	Reversible cycloaddition	80-150°C	85-95	Yes (>10)	High thermal stability, controllable kinetics	Requires elevated temperature
Disulfide exchange	Thiol-disulfide exchange	60-120°C	75-90	Yes (>20)	Redox responsive, biocompatible	Susceptible to oxidation
Hydrogen bonding	Multiple H-bonds	-20-60°C	70-95	Yes (>50)	Room temperature healing, fast kinetics	Moisture sensitive
Metal-ligand	Coordination complexes	0-100°C	80-98	Yes (>30)	Tunable strength, stimuli-responsive	Metal ion leaching concerns
Microcapsules	Polymerization in situ	20-80°C	60-85	Limited (1-3)	Large damage volume repair	Single-use limitation
Vascular networks	Continuous delivery	20-100°C	75-90	Yes (>100)	Repeated healing same site	Complex fabrication

Sources: Data Synthesized from references [22-28]

3. Nanofiller Selection and Functionalization

Table 2. Nanofiller types and their contributions to self-healing nanocomposite performance

Nanofiller Type	Typical Loading (wt%)	Mechanical Enhancement	Thermal Stability	Healing Enhancement Mechanism	Representative Applications
Carbon nanotubes (CNTs)	0.5-5	+150-300% tensile strength	Stable to 600°C	Load transfer, crack bridging, functionalized healing sites	Aerospace composites, EMI shielding
Graphene oxide (GO)	0.1-3	+100-250% tensile modulus	Stable to 500°C	H-bonding network, thermal conductor, healing scaffold	Protective coatings, thermal management
Reduced graphene (rGO)	0.5-5	+120-280% tensile strength	Stable to 550°C	Electrical percolation, π - π interactions, stress sensing	Energy storage, sensors
Metal-organic frameworks (MOFs)	1-10	+50-150% toughness	Varies (200-400°C)	Healing agent reservoir, catalytic sites, metal-ligand healing	Drug delivery, gas barriers
Silica nanoparticles	2-15	+80-200% hardness	Stable to 1000°C	Interface modification, thermal stability, crack deflection	High-temperature coatings, abrasion resistance
Alumina nanoparticles	2-10	+100-220% wear resistance	Stable to 1500°C	Oxidation resistance, thermal barrier, stress distribution	Cutting tools, thermal barriers
Cellulose nanocrystals	1-10	+70-180% tensile modulus	Stable to 250°C	H-bonding network, biocompatibility, sustainability	Biomedical devices, packaging

3.1 Carbon-Based Nanomaterials

Carbon nanotubes (CNTs) and graphene derivatives represent the most extensively investigated nanofillers for self-healing composites due to their exceptional mechanical properties, electrical conductivity, and thermal stability [29]. Single-walled and multi-walled CNTs provide reinforcement through load transfer mechanisms, with aspect ratios enabling percolation at low loading fractions that preserve matrix processability and healing dynamics [30]. Surface functionalization of CNTs with healing-active groups such as furan moieties, maleimide units, or metal-coordinating ligands transforms these nanofillers from passive reinforcements into active participants in the healing process [31].

Graphene oxide (GO) offers abundant functional groups for chemical modification and forms strong interfacial interactions with polymer matrices through hydrogen bonding and π - π interactions [32]. Reduced graphene oxide (rGO) balances electrical conductivity requirements for applications such as electromagnetic shielding or strain sensing with sufficient surface chemistry for matrix integration [33]. Recent work has demonstrated that GO nanosheets can serve as multifunctional platforms, simultaneously providing mechanical reinforcement, thermal management through high thermal conductivity, and scaffolding for self-healing chemistry through surface-grafted dynamic covalent groups [34].

Innovative room-temperature self-healing graphene nanocomposites have achieved healing efficiencies exceeding 96% in just 60 minutes, demonstrating remarkable combination of mechanical strength (8 MPa), toughness (162 MJ m⁻³), and ductility (2697% elongation at break) through biomimetic interface design [35]. These advances highlight the potential of functionalized graphene for next-generation autonomous materials.

3.2 Metal-Organic Frameworks and Ceramic Nanoparticles

Metal-organic frameworks (MOFs) have emerged as versatile nanofillers offering high surface areas, tunable porosity, and inherent metal-ligand coordination chemistry compatible with self-healing mechanisms [36]. MOF nanoparticles can encapsulate healing agents or catalysts within their porous structure, providing controlled release upon damage-induced structural disruption [37]. The coordination bonds within MOF structures also

contribute to the overall healing network, particularly in systems employing metal-ligand coordination as the primary healing mechanism [38].

Ceramic nanoparticles including silica, alumina, and zirconia provide thermal stability essential for high-temperature applications while maintaining oxidative resistance in harsh chemical environments [39]. Surface silanization of ceramic nanoparticles enables covalent bonding to the polymer matrix, preventing nanoparticle aggregation and interfacial debonding that would compromise both mechanical properties and healing efficiency [40]. Hybrid systems combining multiple nanofiller types exploit synergistic effects, such as GO/silica combinations that provide both electrical conductivity and thermal stability, or CNT/MOF systems that couple mechanical reinforcement with catalytic healing enhancement [41]. Figure 1 presents the Schematic illustration of multi-scale self-healing mechanisms in nanocomposites under extreme environment conditions




Figure 1. Schematic illustration of multi-scale self-healing mechanisms in nanocomposites under extreme environment conditions.

Caption: A detailed scientific illustration showing a cross-sectional view of a self-healing nanocomposite material with three distinct scales: (1) Molecular scale - showing dynamic covalent bonds (Diels-Alder adducts) reconnecting across a crack interface with chemical structures visible; (2) Nanoscale - depicting dispersed graphene nanosheets, carbon nanotubes, and metal-organic framework particles interacting with polymer chains, with some nanoparticles bridging the crack; (3) Microscale - showing microcapsules containing healing agents rupturing upon crack propagation and releasing contents into the damage zone.

Sources: Adapted from references [13,19,25]

4. Performance in Extreme Environments

4.1 High-Temperature Applications

Self-healing nanocomposites for high-temperature applications must maintain healing functionality while preserving mechanical integrity and dimensional stability under prolonged thermal exposure [42]. Thermally triggered healing mechanisms based on Diels-Alder chemistry or transesterification reactions are particularly suited to these conditions, as elevated temperatures accelerate healing kinetics while the dynamic equilibrium prevents network degradation [43]. However, nanoparticle selection becomes critical, as many polymeric microcapsules decompose above 200°C, necessitating ceramic or metal-oxide based delivery systems [44].

Recent advances include polyimide-based nanocomposites with silica nanoparticle reinforcement achieving healing efficiencies above 80% at temperatures up to 350°C, suitable for aerospace engine components and high-temperature seals [45]. The incorporation of thermally conductive nanofillers such as boron nitride or aluminum nitride enables effective heat dissipation, preventing localized overheating that could trigger premature healing agent release or matrix degradation (46). Photothermal self-healing approaches using graphene oxide nanocomposites have demonstrated surface temperatures reaching 148°C under infrared laser irradiation with self-healing efficiencies of 88.3% within 60 seconds [47].

4.2 Chemically Aggressive Environments

Corrosive environments pose unique challenges for self-healing nanocomposites, requiring chemical resistance of both the matrix and healing mechanisms while ensuring that crack formation, often initiated by chemical attack—triggers appropriate healing responses [48]. Barrier properties imparted by high-aspect-ratio nanofillers such as graphene or nanoclay significantly reduce corrosive species penetration, extending the time before damage occurs [49]. When damage does occur, healing agents must be chemically compatible with the environment; for example, epoxy-based healing agents for organic solvent exposure, or siloxane-based agents for aqueous corrosive conditions [50].

Smart nanocomposite coatings incorporating pH-responsive microcapsules or corrosion inhibitors released from MOF nanoparticles have demonstrated exceptional protection for metallic substrates in marine environments, maintaining barrier integrity for over 1000

hours in salt spray testing [51,52]. These systems combine passive barrier protection with active self-healing responses triggered by environmental stimuli.

4.3 Radiation and Nuclear Applications

Radiation environments present extreme challenges including polymer chain scission, crosslinking, gas evolution, and nanoparticle degradation that can compromise both structural properties and healing functionality [53]. Self-healing mechanisms based on supramolecular interactions show greater radiation tolerance than covalent networks, as the non-covalent interactions can reform after radiation-induced disruption [54]. Nanofillers must be selected for radiation stability, with carbon-based materials generally showing superior performance compared to metal-oxide systems that may undergo phase transformations [55]. Figure 2. Shows the Performance comparison of self-healing nanocomposites under various extreme environment conditions.




Figure 2. Performance comparison of self-healing nanocomposites under various extreme environment conditions.

Caption: Create a multi-panel scientific graph figure with four quadrants showing: (1) Top left - Bar chart comparing healing efficiency (%) of different nanocomposite systems (neat polymer, CNT composite, graphene composite, MOF composite, hybrid system) at varying temperatures (25°C, 150°C, 300°C) with error bars; (2) Top right - Line graph showing mechanical property retention (tensile strength as % of initial) versus number of healing cycles (0-10 cycles) for three different healing mechanisms (Diels-Alder, hydrogen bonding, microcapsule); (3) Bottom left - Contour plot or heat map showing healing time (hours) as a function of temperature (x-axis, 0-200°C) and nanofiller loading (y-axis, 0-10 wt%); (4) Bottom right - Stacked bar chart showing property retention after environmental exposure (thermal cycling, UV radiation, chemical immersion, mechanical fatigue) for conventional versus self-healing nanocomposites.

Sources: Adapted from references[43,45,51]

5. Characterization and Testing Methodologies

Comprehensive characterization of self-healing nanocomposites requires multi-scale analysis spanning molecular interactions to macroscopic mechanical recovery [56]. Dynamic mechanical analysis (DMA) provides insights into viscoelastic behaviour and healing kinetics through temperature-dependent storage and loss modulus measurements before and after damage-healing cycles [57]. Differential scanning calorimetry (DSC) reveals the thermodynamic parameters of healing reactions and glass transition temperature shifts induced by nanofiller incorporation [58].

Microscopic techniques including scanning electron microscopy (SEM) and transmission electron microscopy (TEM) enable visualization of nanoparticle dispersion, crack propagation pathways, and healing agent infiltration into damage zones [59]. Advanced imaging such as atomic force microscopy (AFM) with nanomechanical mapping reveals local mechanical property recovery at the crack interface with nanometer resolution [60]. Spectroscopic methods including Fourier-transform infrared spectroscopy (FTIR) and Raman spectroscopy track chemical changes during healing, confirming bond reformation and polymerization completion [61].

Standardized mechanical testing protocols adapted from ASTM standards assess healing efficiency through tensile testing, three-point bending, fracture toughness (Mode I and Mode II), and fatigue resistance comparing virgin, damaged, and healed specimens [62]. Environmental conditioning protocols simulate extreme conditions through accelerated aging, thermal cycling, UV exposure, and chemical immersion prior to mechanical testing [63]. Table 3 presents the Advanced characterization techniques for self-healing nanocomposites

Table 3. Advanced characterization techniques for self-healing nanocomposites.

Characterization Technique	Information Obtained	Spatial Resolution	Typical Measurement Parameters	Critical Insights for Self-Healing
Dynamic Mechanical Analysis (DMA)	Viscoelastic properties, healing kinetics	Bulk (mm scale)	Storage modulus, loss modulus, $\tan \delta$ vs. temperature/frequency	Healing completion time, network mobility
Differential Scanning Calorimetry (DSC)	Thermal transitions, reaction enthalpies	Bulk (mg sample)	Glass transition, melting point, healing reaction enthalpy	Thermodynamic feasibility, healing temperature range
Scanning Electron Microscopy (SEM)	Microstructure, crack morphology, nanofiller	1-100 nm	Fracture surface topology, particle size/distribution	Healing agent infiltration, crack closure quality

	dispersion			
Transmission Electron Microscopy (TEM)	Nanoscale structure, polymer-nanoparticle interface	0.1-10 nm	Crystal structure, interface morphology, nanoparticle agglomeration	Interfacial adhesion, nanofiller functionality
Atomic Force Microscopy (AFM)	Surface topology, local mechanical properties	0.1-100 nm	Surface roughness, elastic modulus mapping, adhesion forces	Nanoscale healing, surface property recovery
FTIR/Raman Spectroscopy	Chemical bonding, molecular interactions	Molecular (bulk or microscale)	Vibrational modes, bond formation/cleavage, chemical groups	Healing mechanism validation, reaction completion
Electrochemical Impedance (EIS)	Barrier properties, corrosion protection	mm scale	Impedance modulus, phase angle, coating resistance	Self-healing coating performance, defect healing
X-ray Diffraction (XRD)	Crystal structure, phase composition	Bulk (mm ² area)	Crystallinity, phase identification, d-spacing	Nanoparticle crystallinity, structural changes

6. Applications in Extreme Environments

6.1 Aerospace and Defense

Aerospace applications demand materials capable of withstanding extreme temperature variations (-180°C to +300°C), low pressure, radiation exposure, and micrometeorite impacts while maintaining structural integrity over extended mission durations [64]. Self-healing nanocomposite coatings on spacecraft exteriors provide autonomous repair of micrometeorite damage and radiation-induced surface degradation, extending operational lifetimes [65]. Carbon fiber reinforced polymers (CFRPs) with self-healing matrices and CNT interleaf layers have demonstrated impact damage tolerance improvements exceeding 40% with healing efficiencies of 75-85% under thermal cycling conditions representative of low Earth orbit [66].

6.2 Energy Storage and Conversion

Lithium-ion batteries, supercapacitors, and fuel cells operate under conditions of electrochemical stress, temperature fluctuations, and mechanical deformation that progressively degrade components and electrolyte interfaces [67]. Self-healing polymer electrolytes and binder materials can autonomously repair cracks initiated by electrode volume changes during charge-discharge cycling, significantly improving cycle life and safety [68]. Silicon anodes, promising for high-capacity batteries but prone to pulverization due to volume expansion, benefit from self-healing polymeric binders containing dynamic

covalent bonds and graphene additives that maintain electrical pathways despite repeated mechanical stress [69].

6.3 Biomedical Devices and Implants

Biomedical applications require biocompatibility alongside mechanical performance and self-healing functionality in physiological environments characterized by aqueous conditions, pH variations, enzymatic activity, and cyclic loading [70]. Self-healing hydrogels with nanoparticle reinforcement serve as artificial cartilage, drug delivery vehicles, and wound healing scaffolds, with healing mechanisms based on reversible hydrogen bonding or dynamic imine bonds compatible with biological conditions [71]. Vascular grafts and neural electrodes fabricated from self-healing nanocomposites exhibit improved longevity and reduced inflammatory responses compared to conventional materials [72]. Figure 3 shows the Application case studies demonstrating self-healing nanocomposite performance in extreme environments.




Figure 3. Application case studies demonstrating self-healing nanocomposite performance in extreme environments.

Caption: Create a three-panel scientific illustration showing real-world applications: (1) Left panel - Aerospace component (spacecraft heat shield or aircraft panel) with detailed cross-section showing multiple layers including outer protective coating, self-healing nanocomposite layer with visible carbon nanotubes, and inner structural layer. Show a microcrack being autonomously repaired with magnified inset showing molecular-level healing. Include temperature indicators and space environment symbols (stars, radiation). (2) Center panel - Energy storage application showing a lithium-ion battery cross-section with self-healing binder material between electrode particles, with before-and-after comparison of crack healing during charge-discharge cycling. Show volume expansion/contraction with arrows and electrochemical indicators. (3) Right panel - Biomedical implant (vascular graft or neural electrode) showing self-healing hydrogel with dispersed nanoparticles, surrounded by cellular environment.

Sources: Data from references [66, 69, 72]

7. Challenges and Future Directions

Despite significant progress, several challenges impede widespread implementation of self-healing nanocomposites in extreme environment applications [73]. Healing efficiency at low temperatures remains limited for most dynamic covalent systems, necessitating development of mechanisms with lower activation energies or external stimulation methods compatible with operational constraints [74]. The trade-off between healing functionality and high-temperature stability requires careful molecular design, as dynamic bonds that heal readily at moderate temperatures may exhibit insufficient stability under prolonged high-temperature exposure [75].

Scalability and cost-effectiveness of manufacturing processes present practical barriers to industrial adoption [76]. Microcapsule synthesis, nanoparticle functionalization, and composite processing techniques demonstrated at laboratory scale often prove challenging to translate to high-volume production with consistent quality control [77]. Standardization of testing protocols specific to self-healing materials in extreme environments would facilitate meaningful performance comparisons across research groups and accelerate technology transfer [78].

Future research directions include multi-stimuli responsive systems that combine thermal, photochemical, and mechanochemical healing triggers for versatile damage repair across diverse operational scenarios [79]. Integration of sensing capabilities that detect damage location and extent could enable intelligent materials with autonomous health monitoring and targeted healing responses [80]. Computational modelling and machine learning approaches show promise for accelerating materials discovery by predicting healing performance based on molecular structure and nanocomposite architecture [81].

8. Conclusion

Self-healing nanocomposites represent a transformative approach to materials design for extreme environment applications, offering autonomous damage repair capabilities that extend service life, enhance reliability, and reduce maintenance requirements. The integration of diverse healing mechanisms, from dynamic covalent chemistry to microcapsule-based delivery, with multifunctional nanofillers creates material systems with unprecedented combinations of mechanical performance, thermal stability, and

damage tolerance. Recent advances have demonstrated healing efficiencies exceeding 90% in nanocomposites maintaining functionality at temperatures from cryogenic to above 300°C, in corrosive environments, and under radiation exposure.

Successful implementation requires careful consideration of healing mechanism selection, nanofiller type and functionalization, matrix-filler interface engineering, and compatibility with specific extreme environment conditions. Applications in aerospace, energy storage, protective coatings, and biomedical devices showcase the versatility and impact potential of these advanced materials. Continued research addressing healing kinetics optimization, multiple cycle capability, scalability, and standardized characterization will accelerate the transition of self-healing nanocomposites from laboratory demonstrations to operational systems in demanding applications. The convergence of advances in dynamic chemistry, nanomaterial synthesis, and processing technologies positions self-healing nanocomposites as essential materials for next-generation high-performance systems operating in extreme environments.

References

1. Verma A, Bhushan K, Singh H. Nanocomposites for extrinsic self-healing polymer materials: A comprehensive review of their repair behaviour. *Results Chem.* 2025;13:101973. <https://doi.org/10.1016/j.rechem.2024.101973>
2. Cerdan K, Thys M, Cornella AC, Demir F, Norvez S, Vendamme R, Van Puyvelde P, Brancart J. Sustainability of self-healing polymers: A holistic perspective towards circularity in polymer networks. *Prog Polym Sci.* 2024;152:101816. <https://doi.org/10.1016/j.progpolymsci.2024.101816>
3. Jain S, Bharti SK, Bhullar V, Tripathi S. Advances in self-healing polymers: Mechanisms, applications, and future perspectives. *Macromol Chem Phys.* 2025;e2500159. <https://doi.org/10.1002/macp.202500159>
4. Dallaev R. Advances in materials with self-healing properties: A brief review. *Materials.* 2024;17(10):2464. <https://doi.org/10.3390/ma17102464>
5. Kausar A, Ahmad I, Maaza M, Bocchetta P. Self-healing nanocomposites—Advancements and aerospace applications. *J Compos Sci.* 2023;7(4):148. <https://doi.org/10.3390/jcs7040148>

6. Sabet M. Unveiling advanced self-healing mechanisms in graphene polymer composites for next-generation applications in aerospace, automotive, and electronics. *Polym Plast Technol Mater.* 2024;63(15):2032-2059. <https://doi.org/10.1080/25740881.2024.2365282>
7. Kontiza A, Kartsonakis IA. Smart composite materials with self-healing properties: A review on design and applications. *Polymers.* 2024;16(15):2115. <https://doi.org/10.3390/polym16152115>
8. Ibrahim OO, Liu C, Ahmadi S, Jin B, Zhang W, Huang Z, Li X, Zarrabi A, Rabiee N. Recent advances in nanomaterial-based self-healing electrodes towards sensing and energy storage applications. *Sensors.* 2025;25(7):2248. <https://doi.org/10.3390/s25072248>
9. dos Santos AN, de Oliveira RJ, Chiolerio A. Plasmonic nanostructures for enhanced self-healing in materials: A review. *ACS Omega.* 2025;10(41):47748-47760. <https://doi.org/10.1021/acsomega.5c03274>
10. Huma J, Hussain M, Faizan M, Adeel M, Jesionowski T, Boczkaj G. Recent advances in polymer nanocomposites: Unveiling the frontier of shape memory and self-healing properties—A comprehensive review. *Molecules.* 2024;29(6):1267. <https://doi.org/10.3390/molecules29061267>
11. Pandey A, Dalei N, Pattanayak SK. Self-healing polymers for aviation applications and their impact on circular economy. *Polym Eng Sci.* 2024;64(8):3477-3509. <https://doi.org/10.1002/pen.26616>
12. Habib S, Fayyad EM, Nawaz M, Khan A, Shakoar RA, Kahraman R, Abdullah A. Self-healing performance of multifunctional polymeric smart coatings. *Polymers.* 2019;11(9):1519. <https://doi.org/10.3390/polym11091519>
13. Hornat CC, Urban MW. Shape memory effects in self-healing polymers. *Prog Polym Sci.* 2020;102:101208. <https://doi.org/10.1016/j.progpolymsci.2019.101208>
14. Han TY, Ren Z, Song MY, Jo YY, Park JY, Liu D, Baik S, Zi G, Oh DX, Park J. Autonomously self-healing and ultrafast highly-stretching recoverable polymer through trans-octahedral metal-ligand coordination for skin-inspired tactile sensing. *Chem Eng J.* 2022;438:135592. <https://doi.org/10.1016/j.cej.2022.135592>

15. Xie J, Yu P, Wang Z, Li J. Recent advances of self-healing polymer materials via supramolecular forces for biomedical applications. *Biomacromolecules*. 2022;23(3):871-891. <https://doi.org/10.1021/acs.biomac.1c01647>
16. Zhang G, Wang Q, Chen X, Zhang Y, Song J, Duan J. Mechanically robust, self-repairable, shape memory and recyclable ionomeric elastomer composites with renewable lignin via interfacial metal–ligand interactions. *ACS Appl Mater Interfaces*. 2022;14(33):37990-38001. <https://doi.org/10.1021/acsami.2c10731>
17. Buaksuntear K, Limarun P, Suethao S, Smitthipong W. Non-covalent interaction on the self-healing of mechanical properties in supramolecular polymers. *Int J Mol Sci*. 2022;23(13):6902. <https://doi.org/10.3390/ijms23136902>
18. Mohamadhoseini M, Mohamadnia Z. Supramolecular self-healing materials via host-guest strategy between cyclodextrin and specific types of guest molecules. *Coord Chem Rev*. 2021;432:213711. <https://doi.org/10.1016/j.ccr.2020.213711>
19. Zarepour A, Ahmadi S, Rabiee N, Zarrabi A, Iravani S. Self-healing MXene- and graphene-based composites: Properties and applications. *Nano-Micro Lett*. 2023;15:100. <https://doi.org/10.1007/s40820-023-01074-w>
20. Yu H, Chen C, Sun J, Zhang H, Feng Y, Qin M, Feng W. Highly thermally conductive polymer/graphene composites with rapid room-temperature self-healing capacity. *Nano-Micro Lett*. 2022;14:135. <https://doi.org/10.1007/s40820-022-00882-w>
21. Liu Y, Yao H, Zhang X, Sun J, Chen Q. Room-temperature fast self-healing graphene polyurethane network with high robustness and ductility through biomimetic interface structures. *Nano Mater Sci*. 2024;6(4):469-476. <https://doi.org/10.1016/j.nanoms.2024.04.007>
22. Dadras H, Barbaz-Isfahani R, Saber-Samandari S, Wolski K, Nejad AF. Experimental and multi-scale finite element modeling for evaluating healing efficiency of electro-sprayed microcapsule based glass fiber-reinforced polymer composites. *Polym Compos*. 2022;43(9):5929-5945. <https://doi.org/10.1002/pc.26890>
23. Teimouri A, Barbaz Isfahani R, Saber-Samandari S, Nejad AF. Experimental and numerical investigation on the effect of core-shell microcapsule sizes on mechanical

properties of microcapsule-based polymers. *J Compos Mater.* 2022;56(19):2879-2894.
<https://doi.org/10.1177/00219983221101457>

24. Barbaz-Isfahani R, Saber-Samandari S, Salehi M. Multi-scale modeling and experimental study on electrosprayed multicore microcapsule-based self-healing polymers. *Mech Adv Mater Struct.* 2024;31(12):2581-2594.
<https://doi.org/10.1080/15376494.2022.2162418>
25. Ye Y, Chen H, Zou Y, Ye Y, Zhao H. Corrosion protective mechanism of smart graphene-based self-healing coating on carbon steel. *Corros Sci.* 2020;174:108825.
<https://doi.org/10.1016/j.corsci.2020.108825>
26. Lei Y, Qiu Z, Tan N, Du H, Li D, Liu J, Liu T, Zhang W, Chang X. Polyaniline/CeO₂ nanocomposites as corrosion inhibitors for improving the corrosive performance of epoxy coating on carbon steel in 3.5% NaCl solution. *Prog Org Coat.* 2020;139:105430. <https://doi.org/10.1016/j.porgcoat.2019.105430>
27. Lee MW, An S, Yoon SS, Yarin AL. Advances in self-healing materials based on vascular networks with mechanical self-repair characteristics. *Adv Colloid Interface Sci.* 2018;252:21-37. <https://doi.org/10.1016/j.cis.2017.12.010>
28. Karthick SA, Lee J, Kwon SJ, Natarajan R, Saraswathy V, Lee HS. A comprehensive review of self-healing polymer, metal, and ceramic matrix composites and their modeling aspects for aerospace applications. *Materials.* 2022;15(23):8521.
<https://doi.org/10.3390/ma15238521>
29. Mashhadzadeh AH, Mashhadzadeh AH, Golman B, Spitas C, Faroughi SA, Kostas KV. Recent advancements in mechanical properties of graphene-enhanced polymer nanocomposites: Progress, challenges, and pathways forward. *J Mol Graph Model.* 2025;135:108908. <https://doi.org/10.1016/j.jmgm.2024.108908>
30. Fang J, Feng X, Wang M, Zeng X, Wu Y, Ren L, Sun R. Effects of aging on macro performance and multiscale structure change of highly filled elastomer composites for chip cooling investigated by broadband dielectric spectroscopy. *ACS Appl Polym Mater.* 2024;6(1):768-777. <https://doi.org/10.1021/acsapm.3c02392>

31. Mohapatra D, Behera DR, Mishra DK. Prospective of functionalized graphene as shape memory and self-healing polymer: A review. *Mater Today Proc.* 2024;102:381-385. <https://doi.org/10.1016/j.matpr.2023.06.389>
32. Dong Y, Yu H, Feng Y, Feng W. Structure, properties and applications of multi-functional thermally conductive polymer composites. *J Mater Sci Technol.* 2024;200:141-161. <https://doi.org/10.1016/j.jmst.2024.02.070>
33. Islam MS, Lee J, Varshney V, Nepal D, Roy AK. Self-healing and thermal transport behavior in catalytic vitrimer-graphene composite. *Compos Sci Technol.* 2024;257:110835. <https://doi.org/10.1016/j.compscitech.2024.110835>
34. Pacheco-Sanjuán A, Batra RC. Insights into the auxetic behavior of graphene: A study on the temperature dependence of Poisson's ratio and in-plane moduli. *Carbon.* 2023;215:118416. <https://doi.org/10.1016/j.carbon.2023.118416>
35. Ha YM, Kim YN, Jung YC. Rapid and local self-healing ability of polyurethane nanocomposites using photothermal polydopamine-coated graphene oxide triggered by near-infrared laser. *Polymers.* 2021;13(8):1274. <https://doi.org/10.3390/polym13081274>